

ABSTRACT

In order to provide a color metallic pigment capable of implementing diverse colors, excellent in finished appearance and weather resistance and manufacturable by a safe and simple manufacturing method, a color metallic pigment comprising metal particles and a single-layer or multilayer coat covering the surface of each metal particle characterized in that at least one layer of the single-layer or multilayer coat is a cobalt coat consisting of an anhydrous oxide film elementally containing cobalt is provided. This cobalt coat preferably contains a compound in composition expressed by at least one type of composition selected from a group consisting of CoO , Co_2O_3 , Co_3O_4 , $n\text{CoO} \cdot m\text{Al}_2\text{O}_3$ and $n\text{CoO} \cdot m\text{SiO}_2$ (n, m : arbitrary positive real numbers).

USPS EXPRESS MAIL
EV 511 024 032 US
SEPTEMBER 30 2004